

CHEMICAL RESISTANCE

RESINWERKS TOPCOATS



Key

- 1 No Impact 2 May Stain, will not degrade if cleaned 3 Stains, clean immediately 4 Not recommended

Chemical	Epoxies			Polyaspartics & Urethanes					Acrylic
	LVL-GUARD PIGMENTED	NOVOLAC	LVL-GUARD CLEAR	KINETIC HS	HDC 100	CRU	Matte Finish WB Urethane	BIO-CEM TC	MMA
Acetic Acid-10%	1	1	1	1	1	1	1	1	1
Acetone	3	3	3	1	1	1	1	1	1
Ammonia-30%	1	1	1	1	1	1	1	1	1
Ammonium Hydroxide-30%	1	1	1	1	1	1	1	1	1
Antifreeze	1	1	1	1	1	1	1	1	1
Benzene	4	2	4	1	1	1	1	4	1
Betadine-10%	3	2	3	2	2	2	2	2	2
Boric Acid-4%	1	1	1	1	1	1	1	1	1
Brake Fluid	3	2	3	2	1	1	1	2	1
Butyl Alcohol	2	1	2	1	1	1	1	2	1
Citric Acid-10%	1	1	1	1	1	1	1	1	1
Citric Acid-20%	2	1	1	1	1	1	1	1	1
Citric Acid-50%	4	1	3	1	1	1	1	1	1
Clorox-10%	2	1	1	1	1	1	1	1	1
Cola-Pepsi	1	1	1	1	1	1	1	1	1
Copper Sulfate	3	2	3	2	2	2	2	2	2
Diesel	1	1	1	1	1	1	1	1	1
D-Limonene	3	1	2	1	1	1	1	1	1
Drano- (sodium hydroxide and aluminum)	4	2	3	1	1	1	1	3	1
Ethanol-95%	4	2	3	2	2	1	2	2	2
Ethyl Acetate	1	1	1	1	1	1	1	1	1
Fluoboric Acid	3	2	3	2	2	2	2	2	2
Formaldehyde-37%	1	1	1	1	1	1	1	1	1
Gasoline	3	1	2	1	1	1	1	2	1
Glycol Ether	4	1	3	1	1	1	1	1	1
Hexane	3	1	2	1	1	1	1	2	1
Hydraulic fluids	3	1	2	2	1	1	1	2	1
Hydrochloric Acid-5%	2	1	2	1	2	2	2	2	2
Hydrochloric Acid-10%	3	1	3	2	2	2	2	2	2
Hydrofluoric Acid-20%	3	2	3	2	3	3	3	3	3
Hydrogen Peroxide-.5%	4	1	3	1	1	1	3	4	1
Isopropanol	2	1	2	2	2	1	2	1	2
Isopropyl Acetate-99%	1	1	1	1	1	1	1	1	1
Jet Fuel	3	2	3	1	1	1	1	1	1
Magnesium Hydroxide	4	3	4	1	1	2	1	3	1
Methyl Ethyl Ketone	3	3	3	1	1	1	1	1	1
Methanol	2	1	2	1	1	1	1	1	1
Mineral Oil	1	1	1	1	1	1	1	1	1
Mineral Spirits	2	2	4	1	2	2	2	2	2
Motor Oil	3	1	3	2	2	3	2	2	2
Mustard, yellow	2	1	2	1	1	1	1	2	1
Nitric Acid-10%	4	1	4	1	1	2	1	1	1
Nitric Acid-20%	4	1	4	1	1	2	1	1	1
Phosphoric Acid-10%	1	1	1	1	1	1	1	1	1
Phosphoric Acid-25%	1	2	3	1	1	1	1	1	1
Propylene Glycol	3	1	2	2	1	1	1	1	1
Red Wine Vinegar	1	1	1	1	1	1	1	1	1
Rescue Animal Facility Cleaner/Disinfectant	2	1	2	1	1	1	3	4	1
Skydrol B	3	2	2	1	1	1	1	2	1
Sodium Chloride	3	1	3	2	2	1	2	4	2
Sodium Hydroxide-50%	2	2	2	2	2	3	2	2	2
Styrene	4	2	4	3	4	3	4	2	4
Sulfuric Acid-10%	2	1	2	1	1	1	1	1	1
Sulfuric Acid-50%	2	1	2	1	1	1	1	1	1
Tri-Sodium Phosphate	2	1	1	1	1	1	1	1	1
Uric Acid	3	1	3	1	1	2	1	2	1

All chemical resistance data based on a minimum cure time of 10 days. Tests completed at 70°F and 50% relative humidity. Test results may vary based on conditions and applications. Tests are for exposure to specific chemicals only and not a combination of multiple chemicals at the same time. Resinwerks in no way offers any warranty based on the aforementioned chemical testing data. For individual chemical resistance application questions, please contact your local Resinwerks representative or contact us directly at (720) 484-5160.

(720) 484-5160
www.resinwerks.com
7205 Gilpin Way #100
Denver, CO 80229